



POOL GUARD POOL PAINT – APPLICATION GUIDELINES.

PoolGuard Pool Paint CANNOT be used where the surface being coated is known to have continuous moisture content and or water seepage and can only be applied to above mentioned surfaces. With such types of surfaces a moisture test needs to be performed before application.

- The surface area to be coated must be completely dry and free of dust and debris.
- Avoid painting in direct sunlight or during the hottest period in the day.
- Application done with using a Mohair roller.
- Always apply at least 2 coats of PoolGuard Pool Paint, after Fibreglas primer layer, and one coat after Marbelite or concrete primer at least 1 layer.
- Allow 4 hours drying time between the 1st and 2nd coat.
- Allow at least 4 days after the final coat before filling.

PREPARATION - MARBELITE/CEMENT POOLS (AFTER DRAINING ALL THE WATER)

- 1) Ensure the surface area is dry and free from moisture or water seepage.
- 2) Perform any necessary repairs e.g. Cracks, Flakes etc. first
- 3) Sanding of surfaces if required, and can be done with 150-180 grit sanding paper, sanding normally done with old pools. Acid wash the pool with a mixture of 1 part pool acid (30%) and 2 parts water, then rinse thoroughly with clean water to remove residual acid, drain and sponge dry any remaining water and leave the surface area to dry out completely. (Minimum of 4 days).
- 4) Mask off areas not to be painted e.g. mosaics, pool lights, weirs and aim-flows etc.
- 5) Apply the Primer coat (1st coat), PoolGuard Pool Paint diluted with 10% PoolGuard thinner.
- 6) **NB!** Stir well with a flat bottom paddle or mechanical mixer before applying.
- 7) Allow at least 3 to 4 hours for the primer coat to dry completely.
- 8) Apply the 2nd paint coat. **NB!** Stir well before applying.
- 9) Allow 4 days for the 2nd coat to cure, before filling with water.